

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Ave, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-CM-29

Recommended values and the “Between Lab” Two Standard Deviations

| | | | |
|-------------------|------------------------------|------------------------|-------------------------------|
| <i>Gold</i> | <i>0.720 g/t ± 0.068 g/t</i> | <i>Certified value</i> | <i>30g FA / ICP or AA</i> |
| <i>Copper</i> | <i>0.742 % ± 0.030 %</i> | <i>Certified value</i> | <i>4-acid / ICP or AA</i> |
| <i>Copper</i> | <i>0.734 % ± 0.044 %</i> | <i>Certified value</i> | <i>Aqua regia / ICP or AA</i> |
| <i>Molybdenum</i> | <i>0.053 % ± 0.004 %</i> | <i>Certified value</i> | <i>4-acid / ICP or AA</i> |
| <i>Molybdenum</i> | <i>0.052 % ± 0.006 %</i> | <i>Certified value</i> | <i>Aqua regia / ICP or AA</i> |
| <i>Sulphur</i> | <i>1.70 % ± 0.05 %</i> | <i>Certified value</i> | <i>Leco</i> |

Note: Standards with an RSD of near or less than 5% are certified; RSD's of between 5% and 15% are Provisional; RSD's over 15% are Indicated. Provisional and Indicated values cannot be used to monitor accuracy with a high degree of certainty.

The certified value and between lab 2SD calculated for each element are done so for a specific analytical procedure. It is inappropriate to apply them to other techniques (eg. geochemical analyses).

PREPARED BY: CDN Resource Laboratories Ltd.

CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia

INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.

DATE OF CERTIFICATION: February 18, 2013

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone mixer. Splits were taken and sent to 15 laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-CM-29 was prepared from a combination of Au / Cu ores and concentrates.

Approximate chemical composition (from whole rock analysis) is as follows:

| | Percent | | | Percent |
|--------------------------------|---------|--|------------------|---------|
| SiO ₂ | 66.9 | | MgO | 1.9 |
| Al ₂ O ₃ | 12.2 | | K ₂ O | 1.6 |
| Fe ₂ O ₃ | 7.4 | | TiO ₂ | 0.5 |
| CaO | 2.9 | | LOI | 2.9 |
| Na ₂ O | 2.3 | | S | 1.7 |

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ±2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

REFERENCE MATERIAL CDN-CM-29

Results from round-robin assaying:

| | Lab 1 | Lab 2 | Lab 3 | Lab 4 | Lab 5 | Lab 6 | Lab 7 | Lab 8 | Lab 9 | Lab 10 | Lab 11 | Lab 12 | Lab 13 | Lab 14 | Lab 15 |
|------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t |
| CM-29-1 | 0.702 | 0.697 | 0.791 | 0.703 | 0.71 | 0.783 | 0.75 | 0.773 | 0.71 | 0.691 | 0.74 | 0.655 | 0.748 | 0.696 | 0.695 |
| CM-29-2 | 0.755 | 0.755 | 0.754 | 0.680 | 0.76 | 0.708 | 0.74 | 0.730 | 0.73 | 0.716 | 0.72 | 0.671 | 0.689 | 0.747 | 0.707 |
| CM-29-3 | 0.683 | 0.723 | 0.743 | 0.643 | 0.72 | 0.745 | 0.78 | 0.725 | 0.71 | 0.784 | 0.74 | 0.680 | 0.677 | 0.740 | 0.705 |
| CM-29-4 | 0.693 | 0.730 | 0.720 | 0.741 | 0.71 | 0.713 | 0.77 | 0.704 | 0.68 | 0.750 | 0.74 | 0.643 | 0.666 | 0.695 | 0.697 |
| CM-29-5 | 0.721 | 0.689 | 0.777 | 0.704 | 0.76 | 0.737 | 0.73 | 0.674 | 0.72 | 0.715 | 0.82 | 0.677 | 0.676 | 0.721 | 0.692 |
| CM-29-6 | 0.792 | 0.649 | 0.786 | 0.750 | 0.73 | 0.777 | 0.73 | 0.729 | 0.72 | 0.796 | 0.72 | 0.664 | 0.740 | 0.679 | 0.715 |
| CM-29-7 | 0.718 | 0.734 | 0.762 | 0.815 | 0.71 | 0.675 | 0.72 | 0.693 | 0.68 | 0.786 | 0.72 | 0.675 | 0.776 | 0.751 | 0.714 |
| CM-29-8 | 0.739 | 0.800 | 0.768 | 0.718 | 0.72 | 0.720 | 0.75 | 0.705 | 0.68 | 0.773 | 0.73 | 0.661 | 0.783 | 0.709 | 0.705 |
| CM-29-9 | 0.661 | 0.701 | 0.788 | 0.725 | 0.74 | 0.662 | 0.75 | 0.693 | 0.70 | 0.785 | 0.73 | 0.675 | 0.675 | 0.724 | 0.690 |
| CM-29-10 | 0.703 | 0.668 | 0.754 | 0.727 | 0.71 | 0.726 | 0.69 | 0.748 | 0.72 | 0.744 | 0.73 | 0.684 | 0.730 | 0.701 | 0.697 |
| Mean | 0.717 | 0.715 | 0.764 | 0.721 | 0.727 | 0.725 | 0.741 | 0.717 | 0.705 | 0.754 | 0.739 | 0.669 | 0.716 | 0.716 | 0.702 |
| Std. Devn. | 0.0378 | 0.0438 | 0.0225 | 0.0454 | 0.0200 | 0.0388 | 0.0256 | 0.0294 | 0.0190 | 0.0366 | 0.0296 | 0.0127 | 0.0446 | 0.0243 | 0.0088 |
| % RSD | 5.27 | 6.12 | 2.94 | 6.29 | 2.75 | 5.35 | 3.45 | 4.10 | 2.70 | 4.85 | 4.01 | 1.90 | 6.23 | 3.40 | 1.26 |
| | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | |
| 4 Acid | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu |
| CM-29-1 | 0.738 | 0.766 | 0.743 | 0.712 | 0.759 | 0.713 | 0.741 | 0.734 | 0.77 | 0.750 | 0.758 | 0.797 | 0.749 | 0.744 | 0.74 |
| CM-29-2 | 0.743 | 0.761 | 0.746 | 0.725 | 0.765 | 0.733 | 0.727 | 0.730 | 0.76 | 0.743 | 0.751 | 0.757 | 0.752 | 0.741 | 0.75 |
| CM-29-3 | 0.746 | 0.726 | 0.783 | 0.721 | 0.736 | 0.719 | 0.734 | 0.728 | 0.77 | 0.754 | 0.763 | 0.785 | 0.748 | 0.727 | 0.75 |
| CM-29-4 | 0.740 | 0.728 | 0.768 | 0.713 | 0.760 | 0.728 | 0.731 | 0.721 | 0.77 | 0.757 | 0.759 | 0.779 | 0.749 | 0.727 | 0.75 |
| CM-29-5 | 0.741 | 0.729 | 0.760 | 0.728 | 0.754 | 0.736 | 0.738 | 0.725 | 0.77 | 0.753 | 0.747 | 0.775 | 0.746 | 0.725 | 0.74 |
| CM-29-6 | 0.749 | 0.731 | 0.774 | 0.722 | 0.742 | 0.739 | 0.740 | 0.737 | 0.77 | 0.753 | 0.758 | 0.811 | 0.749 | 0.725 | 0.75 |
| CM-29-7 | 0.750 | 0.716 | 0.751 | 0.736 | 0.773 | 0.726 | 0.726 | 0.719 | 0.78 | 0.761 | 0.748 | 0.809 | 0.744 | 0.756 | 0.74 |
| CM-29-8 | 0.756 | 0.733 | 0.753 | 0.723 | 0.767 | 0.713 | 0.725 | 0.727 | 0.75 | 0.750 | 0.735 | 0.774 | 0.746 | 0.731 | 0.74 |
| CM-29-9 | 0.750 | 0.762 | 0.712 | 0.726 | 0.771 | 0.702 | 0.731 | 0.719 | 0.76 | 0.752 | 0.754 | 0.782 | 0.737 | 0.731 | 0.74 |
| CM-29-10 | 0.727 | 0.727 | 0.735 | 0.731 | 0.779 | 0.760 | 0.734 | 0.736 | 0.77 | 0.758 | 0.742 | 0.779 | 0.743 | 0.722 | 0.75 |
| Mean | 0.744 | 0.738 | 0.753 | 0.724 | 0.761 | 0.727 | 0.733 | 0.728 | 0.767 | 0.753 | 0.751 | 0.785 | 0.746 | 0.733 | 0.745 |
| Std. Devn. | 0.0081 | 0.0179 | 0.0205 | 0.0074 | 0.0136 | 0.0164 | 0.0058 | 0.0067 | 0.0082 | 0.0050 | 0.0087 | 0.0166 | 0.0042 | 0.0110 | 0.0053 |
| % RSD | 1.09 | 2.43 | 2.72 | 1.02 | 1.78 | 2.26 | 0.80 | 0.92 | 1.07 | 0.66 | 1.16 | 2.12 | 0.57 | 1.50 | 0.71 |
| | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | |
| Aqua regia | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu | % Cu |
| CM-29-1 | 0.752 | 0.735 | 0.729 | 0.724 | 0.754 | 0.755 | 0.702 | 0.708 | 0.81 | 0.729 | 0.697 | 0.780 | 0.743 | 0.740 | 0.74 |
| CM-29-2 | 0.749 | 0.719 | 0.698 | 0.719 | 0.757 | 0.754 | 0.715 | 0.719 | 0.74 | 0.645 | 0.696 | 0.775 | 0.750 | 0.732 | 0.73 |
| CM-29-3 | 0.748 | 0.694 | 0.747 | 0.726 | 0.762 | 0.766 | 0.669 | 0.715 | 0.77 | 0.715 | 0.692 | 0.755 | 0.743 | 0.722 | 0.74 |
| CM-29-4 | 0.747 | 0.711 | 0.702 | 0.732 | 0.757 | 0.762 | 0.735 | 0.713 | 0.78 | 0.722 | 0.699 | 0.731 | 0.741 | 0.734 | 0.73 |
| CM-29-5 | 0.756 | 0.725 | 0.735 | 0.732 | 0.775 | 0.758 | 0.720 | 0.697 | 0.76 | 0.717 | 0.706 | 0.727 | 0.741 | 0.729 | 0.74 |
| CM-29-6 | 0.736 | 0.723 | 0.723 | 0.737 | 0.770 | 0.759 | 0.752 | 0.714 | 0.79 | 0.675 | 0.695 | 0.773 | 0.743 | 0.716 | 0.73 |
| CM-29-7 | 0.733 | 0.718 | 0.722 | 0.722 | 0.767 | 0.753 | 0.725 | 0.699 | 0.79 | 0.723 | 0.683 | 0.728 | 0.740 | 0.729 | 0.74 |
| CM-29-8 | 0.751 | 0.709 | 0.727 | 0.732 | 0.749 | 0.753 | 0.732 | 0.700 | 0.78 | 0.598 | 0.705 | 0.746 | 0.735 | 0.755 | 0.74 |
| CM-29-9 | 0.747 | 0.728 | 0.714 | 0.712 | 0.768 | 0.748 | 0.668 | 0.708 | 0.77 | 0.689 | 0.701 | 0.778 | 0.746 | 0.747 | 0.74 |
| CM-29-10 | 0.748 | 0.718 | 0.699 | 0.731 | 0.753 | 0.757 | 0.726 | 0.705 | 0.76 | 0.698 | 0.701 | 0.748 | 0.748 | 0.729 | 0.74 |
| Mean | 0.747 | 0.718 | 0.720 | 0.727 | 0.761 | 0.757 | 0.714 | 0.708 | 0.775 | 0.691 | 0.697 | 0.754 | 0.743 | 0.733 | 0.737 |
| Std. Devn. | 0.0070 | 0.0114 | 0.0163 | 0.0076 | 0.0085 | 0.0051 | 0.0275 | 0.0075 | 0.0196 | 0.0418 | 0.0067 | 0.0213 | 0.0043 | 0.0116 | 0.0048 |
| % RSD | 0.94 | 1.59 | 2.26 | 1.04 | 1.12 | 0.67 | 3.85 | 1.06 | 2.53 | 6.05 | 0.97 | 2.83 | 0.57 | 1.58 | 0.66 |

Note: Four acid Cu results from Lab 12 were removed for failing the t test.

REFERENCE MATERIAL CDN-CM-29

Results from round-robin assaying:

| | Lab 1 | Lab 2 | Lab 3 | Lab 4 | Lab 5 | Lab 6 | Lab 7 | Lab 8 | Lab 9 | Lab 10 | Lab 11 | Lab 12 | Lab 13 | Lab 14 | Lab 15 |
|------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| 4 Acid | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % |
| CM-29-1 | 0.054 | 0.059 | 0.051 | 0.050 | 0.053 | 0.050 | 0.054 | 0.051 | 0.05 | 0.055 | 0.055 | 0.054 | 0.055 | 0.052 | 0.06 |
| CM-29-2 | 0.054 | 0.057 | 0.053 | 0.051 | 0.053 | 0.052 | 0.051 | 0.053 | 0.05 | 0.054 | 0.055 | 0.050 | 0.055 | 0.052 | 0.05 |
| CM-29-3 | 0.055 | 0.055 | 0.054 | 0.051 | 0.054 | 0.052 | 0.053 | 0.053 | 0.05 | 0.055 | 0.055 | 0.052 | 0.056 | 0.052 | 0.06 |
| CM-29-4 | 0.054 | 0.053 | 0.055 | 0.051 | 0.055 | 0.051 | 0.055 | 0.052 | 0.05 | 0.054 | 0.053 | 0.049 | 0.056 | 0.052 | 0.06 |
| CM-29-5 | 0.054 | 0.056 | 0.054 | 0.052 | 0.054 | 0.053 | 0.054 | 0.052 | 0.05 | 0.055 | 0.051 | 0.051 | 0.055 | 0.051 | 0.06 |
| CM-29-6 | 0.055 | 0.056 | 0.054 | 0.050 | 0.053 | 0.052 | 0.054 | 0.052 | 0.05 | 0.055 | 0.053 | 0.054 | 0.056 | 0.051 | 0.05 |
| CM-29-7 | 0.054 | 0.056 | 0.054 | 0.050 | 0.053 | 0.052 | 0.053 | 0.053 | 0.05 | 0.056 | 0.054 | 0.055 | 0.054 | 0.052 | 0.05 |
| CM-29-8 | 0.055 | 0.055 | 0.054 | 0.051 | 0.053 | 0.050 | 0.052 | 0.051 | 0.05 | 0.056 | 0.052 | 0.052 | 0.057 | 0.052 | 0.06 |
| CM-29-9 | 0.055 | 0.057 | 0.052 | 0.049 | 0.055 | 0.050 | 0.054 | 0.052 | 0.05 | 0.054 | 0.052 | 0.052 | 0.056 | 0.051 | 0.06 |
| CM-29-10 | 0.052 | 0.054 | 0.052 | 0.051 | 0.053 | 0.053 | 0.052 | 0.052 | 0.05 | 0.055 | 0.052 | 0.050 | 0.054 | 0.052 | 0.06 |
| Mean | 0.054 | 0.056 | 0.053 | 0.051 | 0.054 | 0.052 | 0.053 | 0.052 | 0.050 | 0.055 | 0.053 | 0.052 | 0.055 | 0.052 | 0.057 |
| Std. Devn. | 0.0009 | 0.0017 | 0.0012 | 0.0008 | 0.0008 | 0.0013 | 0.0012 | 0.0008 | 0.0000 | 0.0007 | 0.0015 | 0.0018 | 0.0010 | 0.0005 | 0.0048 |
| % RSD | 1.70 | 3.02 | 2.32 | 1.67 | 1.45 | 2.43 | 2.27 | 1.54 | 0.00 | 1.34 | 2.81 | 3.46 | 1.74 | 0.94 | 8.47 |
| | | | | | | | | | | | | | | | |
| Aqua regia | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % | Mo % |
| CM-29-1 | 0.054 | 0.051 | 0.054 | 0.044 | 0.054 | 0.039 | 0.048 | 0.054 | 0.053 | 0.052 | 0.043 | 0.046 | 0.054 | 0.052 | 0.04 |
| CM-29-2 | 0.054 | 0.050 | 0.051 | 0.044 | 0.053 | 0.041 | 0.051 | 0.054 | 0.053 | 0.047 | 0.040 | 0.047 | 0.054 | 0.053 | 0.04 |
| CM-29-3 | 0.055 | 0.051 | 0.055 | 0.046 | 0.055 | 0.042 | 0.047 | 0.055 | 0.054 | 0.054 | 0.038 | 0.045 | 0.053 | 0.050 | 0.04 |
| CM-29-4 | 0.054 | 0.050 | 0.052 | 0.047 | 0.054 | 0.042 | 0.053 | 0.056 | 0.053 | 0.053 | 0.037 | 0.045 | 0.053 | 0.051 | 0.04 |
| CM-29-5 | 0.054 | 0.051 | 0.053 | 0.046 | 0.055 | 0.042 | 0.052 | 0.056 | 0.050 | 0.052 | 0.042 | 0.042 | 0.054 | 0.052 | 0.05 |
| CM-29-6 | 0.052 | 0.053 | 0.053 | 0.046 | 0.055 | 0.043 | 0.053 | 0.055 | 0.052 | 0.049 | 0.040 | 0.046 | 0.054 | 0.052 | 0.05 |
| CM-29-7 | 0.052 | 0.052 | 0.052 | 0.044 | 0.055 | 0.040 | 0.053 | 0.053 | 0.052 | 0.053 | 0.039 | 0.044 | 0.054 | 0.051 | 0.04 |
| CM-29-8 | 0.054 | 0.050 | 0.053 | 0.045 | 0.053 | 0.039 | 0.051 | 0.054 | 0.053 | 0.043 | 0.041 | 0.044 | 0.054 | 0.051 | 0.04 |
| CM-29-9 | 0.054 | 0.050 | 0.052 | 0.045 | 0.055 | 0.040 | 0.046 | 0.055 | 0.054 | 0.049 | 0.040 | 0.047 | 0.054 | 0.052 | 0.05 |
| CM-29-10 | 0.054 | 0.050 | 0.052 | 0.044 | 0.055 | 0.042 | 0.052 | 0.055 | 0.054 | 0.052 | 0.042 | 0.045 | 0.054 | 0.051 | 0.04 |
| Mean | 0.054 | 0.051 | 0.053 | 0.045 | 0.054 | 0.041 | 0.051 | 0.055 | 0.053 | 0.050 | 0.040 | 0.045 | 0.054 | 0.051 | 0.043 |
| Std. Devn. | 0.0009 | 0.0010 | 0.0012 | 0.0013 | 0.0009 | 0.0013 | 0.0026 | 0.0009 | 0.0012 | 0.0034 | 0.0018 | 0.0017 | 0.0004 | 0.0007 | 0.0048 |
| % RSD | 1.77 | 2.03 | 2.21 | 2.79 | 1.72 | 3.25 | 5.15 | 1.68 | 2.33 | 6.76 | 4.55 | 3.77 | 0.78 | 1.33 | 11.23 |
| | | | | | | | | | | | | | | | |
| Leco | S % | S % | S % | S % | S % | S % | S % | S % | S % | S % | S % | S % | S % | S % | S % |
| CM-29-1 | 1.68 | 1.69 | 1.74 | 1.80 | 1.70 | 1.67 | 1.70 | 1.68 | 1.71 | | | 1.86 | 1.71 | 1.87 | 1.67 |
| CM-29-2 | 1.67 | 1.73 | 1.76 | 1.79 | 1.67 | 1.66 | 1.65 | 1.70 | 1.68 | | | 1.83 | 1.70 | 1.84 | 1.68 |
| CM-29-3 | 1.71 | 1.70 | 1.72 | 1.83 | 1.69 | 1.71 | 1.69 | 1.71 | 1.69 | | | 1.85 | 1.71 | 1.85 | 1.69 |
| CM-29-4 | 1.68 | 1.74 | 1.76 | 1.79 | 1.71 | 1.67 | 1.68 | 1.70 | 1.68 | | | 1.83 | 1.72 | 1.90 | 1.67 |
| CM-29-5 | 1.67 | 1.72 | 1.73 | 1.81 | 1.68 | 1.70 | 1.64 | 1.70 | 1.68 | | | 1.82 | 1.72 | 1.90 | 1.71 |
| CM-29-6 | 1.67 | 1.71 | 1.75 | 1.82 | 1.70 | 1.68 | 1.69 | 1.68 | 1.70 | | | 1.83 | 1.73 | 1.84 | 1.68 |
| CM-29-7 | 1.68 | 1.72 | 1.73 | 1.83 | 1.71 | 1.70 | 1.65 | 1.71 | 1.69 | | | 1.84 | 1.74 | 1.89 | 1.67 |
| CM-29-8 | 1.69 | 1.68 | 1.72 | 1.83 | 1.70 | 1.72 | 1.65 | 1.69 | 1.71 | | | 1.84 | 1.72 | 1.89 | 1.67 |
| CM-29-9 | 1.62 | 1.76 | 1.73 | 1.81 | 1.71 | 1.72 | 1.65 | 1.72 | 1.70 | | | 1.86 | 1.74 | 1.82 | 1.66 |
| CM-29-10 | 1.63 | 1.71 | 1.72 | 1.82 | 1.72 | 1.70 | 1.65 | 1.69 | 1.68 | | | 1.82 | 1.74 | 1.86 | 1.69 |
| Mean | 1.67 | 1.72 | 1.74 | 1.81 | 1.70 | 1.69 | 1.67 | 1.70 | 1.69 | | | 1.84 | 1.72 | 1.87 | 1.68 |
| Std. Devn. | 0.0267 | 0.0237 | 0.0158 | 0.0157 | 0.0152 | 0.0216 | 0.0222 | 0.0132 | 0.0123 | | | 0.0148 | 0.0142 | 0.0284 | 0.0145 |
| % RSD | 1.60 | 1.38 | 0.91 | 0.86 | 0.90 | 1.28 | 1.34 | 0.78 | 0.73 | | | 0.80 | 0.82 | 1.52 | 0.86 |

**Note: Four acid Mo results from Lab 15 were removed for failing the t test.
Aqua regia Mo results from Labs 6, 11 and 15 were removed for failing the t test.
Leco sulphur results from Labs 4, 12 and 14 were removed for failing the t test.
Labs 10 and 11 were unable to supply Leco sulphur results.**

REFERENCE MATERIAL CDN-CM-29

Participating Laboratories:


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver, B.C., Canada
Acme Analytical Laboratories Ltd., Santiago, Chile
Actlabs, Ancaster, Ontario, Canada
Actlabs, Thunder Bay, Ontario, Canada
AGAT, Mississauga, Ontario, Canada
ALS Canada, North Vancouver, B.C., Canada
ALS (Omac), Northern Ireland
Alex Stewart, Mendoza, Argentina
Certimin, Lima, Peru
Intertek - Genalysis, Perth, Australia
SGS, Lima, Peru
SGS, Toronto, Ontario, Canada
SGS, Vancouver, B.C., Canada
TSL Laboratories, Saskatoon, Canada
Ultra Trace (Bureau Veritas), Perth, Australia


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by


Duncan Sanderson, Certified Assayer of B.C.

Geochemist


Dr. Barry Smee, Ph.D., P. Geo.